

**PRODUCT INFORMATION**

General Grade 40D

**KOPEL<sup>®</sup> KP3340**

Polyester Elastomer Resin, General Grade 40D

Property	Test Method	Units	Value	
<b>Physical</b>				
Specific Gravity	ASTM D792	-	1.15	
Melt Index                      200 °C * 2160g	ASTM D1238	g/10min	17	
Shrinkage	ASTM D955	%	1.1	
Water Absorption    23 °C, Equilibrium 60%RH	ASTM D570	%	0.7	
<b>Thermal</b>				
Melting Point	ASTM D3418	°C	170	
Heat Deflection Temperature under Load HDT/A    0.45 MPa ( 4.6 kg/cm <sup>2</sup> )	ASTM D648	°C	65	
Solenoid Brittle Point	ASTM D746	°C	<-70	
Flammability	UL 94		HB	
<b>Mechanical</b>				
Tensile Strength                      23 °C	ASTM D638	kg/cm <sup>2</sup>	210	
Tensile Elongation                    23 °C	ASTM D638	%	920	
Flexural Modulus                     23 °C	ASTM D790	kg/cm <sup>2</sup>	970	
Notched Izod Impact Strength	23 °C	ASTM D256	kg·cm/cm	N/B
	-40 °C	ASTM D256	kg·cm/cm	N/B
Hardness, Durometer	ASTM D2240	SHORE D-Type	40	
Abrasion Resistance CS-17 Wheel	ASTM D1044	mg/1,000 cycles	3	
Resilience		%	67	

The information provided in this data sheet is based on our present state of knowledge and is estimated by KOLON PLASTICS, Inc. This information should not be used as guaranteeing specification limits. KOLON PLASTICS, Inc. make no warranty and liability in connection with any use of this information.


**KOLON PLASTICS, Inc.**

 KOLON TOWER, 1-23, BYULYANG-DONG, GWACHEON-CITY GYUNG GI-DO, KOREA  
 Tel. 82-2-3677-3580~9 Fax. 82-2-3677-3558